

## Tapiflex Excellence 65

### Specification

Printed vinyl flooring on a glass fibre non woven PVC back coating Polyurethane reinforcement.  
Product standard: ISO 12868 / EN 661.

## Accent Excellence 80

### Specification

Compact flexible vinyl flooring with glass fibre reinforced, printed Polyurethane reinforcement.  
Product standard: ISO 12868 / EN 661.

| DESCRIPTION & CLASSIFICATION |  | PRODUCT  | Tapiflex Excellence 65 (Sheet)   | Tapiflex Tiles 65  | Accent Excellence 80 (Sheet)  | Accent Dark (Sheet)   | Accent Light (Sheet)  |
|------------------------------|--|--|--|--|---|---|---|
| Type of flooring             | ISO 12868 / EN 661                         |  | Heterogeneous Acoustic Vinyl   | Heterogeneous Acoustic Vinyl   | -   | -   | -   |
| Wear Layer Rider Content     | ISO 10042                                  |  | Type 1   | Type 1   | Type 1  | Type 1  | Type 1  |
| LE Certification             | EN 12467                                   |  | Yes  | Yes  | Yes   | Yes   | Yes   |
| Classification               | ISO 10618 - EN 661                         |  | 26   | 26   | 26-27   | 27  | 27  |
| TECHNICAL CHARACTERISTICS    |  | VALUES   | Tapiflex Excellence 65 (Sheet)   | Tapiflex Tiles 65  | Accent Excellence 80 (Sheet)  | Accent Dark (Sheet)   | Accent Light (Sheet)  |
| Surface Treatment            |  |  | TopClear 3P*   | TopClear 3P*   | TopClear 3P*  | TopClear 3P*  | TopClear 3P*  |
| Total thickness              | ISO 12146 - EN 429                         | 2,35 mm  | 2,35 mm  | 2,35 mm  | 2,35 mm   | 2,35 mm   | 2,35 mm   |
| Wear layer thickness         | ISO 12146 - EN 429                         | 0,85 mm  | 0,85 mm  | 0,85 mm  | 0,85 mm   | 0,85 mm   | 0,85 mm   |
| Total weight                 | ISO 12081 - EN 120                         | 2,642 g/sq m   | 2,642 g/sq m   | 2,642 g/sq m   | 2,789 g/sq m  | 2,789 g/sq m  | 2,789 g/sq m  |
| Form of delivery             | ISO 12146 - EN 120 Sheet (m <sup>2</sup> ) | Approx. 23 running metres x 200 cm.  | -  | -  | Approx. 23 running metres x 200 cm.                                     | Approx. 23 running metres x 200 cm.                                     | Approx. 23 running metres x 200 cm.                                     |
|                              | ISO 12146 - EN 120 Tiles (m <sup>2</sup> ) | -  | 60 x 60 cm - 20 Tiles/box x 6,00 m <sup>2</sup>  | -  | -   | -   | -   |
| TECHNICAL PERFORMANCE        |  | VALUES   | Tapiflex Excellence 65 (Sheet)   | Tapiflex Tiles 65  | Accent Excellence 80 (Sheet)  | Accent Dark (Sheet)   | Accent Light (Sheet)  |
| Dimensional stability        | EN 426                                     | +/-0,20%   | +/-0,20%   | +/-0,20%   | +/-0,20%  | +/-0,20%  | +/-0,20%  |
| Resistance to fire           | EN 13501-1                                 | Bs, Cs or d  | Bs, Cs or d on placement substrate A2-s1, d1 or on woodenly substrate B                        | Bs, Cs or d on placement substrate A2-s1, d1 or on woodenly substrate B                        | Bs, Cs or d on placement substrate A2-s1, d1 or on woodenly substrate B | Bs, Cs or d on placement substrate A2-s1, d1 or on woodenly substrate B | Bs, Cs or d on placement substrate A2-s1, d1 or on woodenly substrate B |
| Anti-scratch test            | ISO 12919 - EN 626                         | 0,8 mm   | 0,2 mm   | 0,2 mm   | 0,8 mm  | 0,8 mm  | 0,8 mm  |
| Residual indentation         | ISO 12143-1 - EN 423                       | Required value: < 0,20 mm<br>Average measured value*: 0,20 mm<br>Max. measured value*: 0,20 mm | Required value: < 0,20 mm<br>Average measured value*: 0,22 mm<br>Max. measured value*: 0,25 mm | Required value: < 0,20 mm<br>Average measured value*: 0,22 mm<br>Max. measured value*: 0,25 mm | Required value: < 0,20 mm<br>Average measured value*: 0,20 mm           | Required value: < 0,20 mm<br>Average measured value*: 0,20 mm           | Required value: < 0,20 mm<br>Average measured value*: 0,20 mm           |
| Impact sound reduction       | EN 12514-8<br>EN ISO 1215-2                | ΔL <sub>g</sub> 19 dB  | ΔL <sub>g</sub> 19 dB  | ΔL <sub>g</sub> 19 dB  | ΔL <sub>g</sub> 19 dB   | ΔL <sub>g</sub> 19 dB   | ΔL <sub>g</sub> 19 dB   |
| Acoustical improvement       | EN ISO 1215-2                              | C <sub>w,eq</sub> + 0,0 dB - Class A   | C <sub>w,eq</sub> + 0,0 dB - Class A   | C <sub>w,eq</sub> + 0,0 dB - Class A   | C <sub>w,eq</sub> + 0,0 dB - Class C                                    | C <sub>w,eq</sub> + 0,0 dB - Class B                                    | C <sub>w,eq</sub> + 0,0 dB - Class B                                    |
| Carpet wheel test            | ISO 4918 - EN 425                          | No damage  | No damage  | No damage  | No damage   | No damage   | No damage   |
| Furniture leg                | EN 626                                     | No damage  | No damage  | No damage  | No damage   | No damage   | No damage   |
| Electrostatic properties     | EN 1825<br>EN 1826                         | < 2 kV on concrete<br>0,1 x 10 <sup>11</sup> Ω   | < 2 kV on concrete<br>0,1 x 10 <sup>11</sup> Ω   | < 2 kV on concrete<br>0,1 x 10 <sup>11</sup> Ω   | < 2 kV on concrete<br>0,1 x 10 <sup>11</sup> Ω                          | < 2 kV on concrete<br>0,1 x 10 <sup>11</sup> Ω                          | < 2 kV on concrete<br>0,1 x 10 <sup>11</sup> Ω                          |
| Total VOC emissions          | AENB 026                                   | 0,28 g/m <sup>2</sup> (after 30 days)  | 0,28 g/m <sup>2</sup> (after 30 days)  | 0,28 g/m <sup>2</sup> (after 30 days)  | 0,28 g/m <sup>2</sup> (after 30 days)                                   | 0,28 g/m <sup>2</sup> (after 30 days)                                   | 0,28 g/m <sup>2</sup> (after 30 days)                                   |
| Thermal resistance           | EN 12687                                   | 0,26 m <sup>2</sup> K/W  | 0,26 m <sup>2</sup> K/W  | 0,26 m <sup>2</sup> K/W  | 0,26 m <sup>2</sup> K/W   | 0,26 m <sup>2</sup> K/W   | 0,26 m <sup>2</sup> K/W   |
| Interface heating            | EN 12687                                   | Subtable   | Subtable   | Subtable   | Subtable  | Subtable  | Subtable  |
| Light fastness               | ISO 12018-020                              | 3,5  | 3,5  | 3,5  | 3,5   | 3,5   | 3,5   |
| Chemical resistance          | ISO 12697 - EN 423                         | High resistance  | High resistance  | High resistance  | High resistance   | High resistance   | High resistance   |
| Hygiene                      |  | Does not contribute to infection spreading   | Does not contribute to infection spreading   | Does not contribute to infection spreading   | Does not contribute to infection spreading                              | Does not contribute to infection spreading                              | Does not contribute to infection spreading                              |
| Slip resistance              | EN 12130<br>EN 12861                       | RII/EN 1303  | R9   | R9/R10   | R9/R10  | R9/R10  | R9/R10  |
| Colour                       |  | 12,7   | 12,7   | 12,7   | 12,7  | 12,7  | 12,7  |

The above information is subject to modification for the benefit of further information. (20/24). \*No application - not binding

Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address chosen for these instructions.

CUSTOMER CARE + 48 (2) 60003007

Do not discard vinyl scraps into the soil. Do not use vinyl scraps in water supply systems and in food contact applications.



**WETFOAM GROUP:** Austria: Tarkett-Holding GmbH, Wien/Leopoldsdorf - Tel.: +43 1 47 68 302 • Belgium: Tarkett-Floor-Union B.V. - Tel.: +32 34 34 80 60 • Denmark: Tarkett A/S - Tel.: +45 44 99 40 11 • Finland: Tarkett Oy - Tel.: +358 9 4272 9000 • France: Tarkett S.A.S. - Tel.: +33 1 21 20 24 29 • Germany: Tarkett-Holding GmbH, Bietigheim-Bissingen - Tel.: +49 7148 3451 • Hungary: Tarkett Magyarország Ltd. - Tel.: +36 23 45 34 33 • Italy: Tarkett-Flooring S.p.A. - Tel.: +39 02 64 24 14 14 • Luxembourg: Tarkett S.A.S. - Tel.: +352 69 11 66 60 • Netherlands: Tarkett-Holding B.V., Overigse Toren 2A - Tel.: +31 77 23 20 20 • Norway: Tarkett-Holding AS, Brønnøysund Sentralby - Tel.: +47 81 54 14 14 • Portugal: Tarkett SA - Tel.: +351 21 427 81 24 • Qatar: Tarkett FSC - Tel.: +974 33 918 919 • Slovenia: Tarkett Group Ltd. - Tel.: +386 71 23 20 20 • Sweden: Tarkett-Holding AB, Brännkyrkavägen 30 - Tel.: +46 20 123 70 24 • Turkey: Tarkett Turkey - Tel.: +90 212 213 04 14 • United Kingdom: Tarkett Ltd. - Tel.: +44 (0) 20 80 80 91 00 • USA: TARKETT GROUP INC., Dallas-Centralplex, Tarkett Building, Inc. - Tel.: +1 972 392 2112 • Canada: Regipolix, Tarkett-France SAS, org. division - Tel.: +33 1 69 151 622 • Hungary: Tarkett-France SAS - Tel.: +33 1 69 151 622 • Poland: Tarkett Polska Sp. z o.o. - Tel.: +48 22 631 14 14 • Romania: Polimex S.R.L. Tarkett-ROU - Tel.: +40 755 375 374 • Slovakia: Tarkett-France SAS, org. division - Tel.: +33 1 69 151 622 • Czech-Rep. Europe: Tarkett Group Ltd. a.s. - Tel.: +420 281 291 211 • United Arab Emirates: Tarkett Middle East - Tel.: +971 21 7607 608 (247 989 12 21) • Ukraine: Tarkett Group - Tel.: +380 044 44 588 12 21

**ISO 14001 and ISO 18001:** Australia: Tarkett Australia Pty Ltd. - Tel.: +61 8 839 12 12 • China: Tarkett Floor Covering (Shanghai) Co. Ltd. - Tel.: +86 21 51 80 80 80 • India: Tarkett India Pvt. Ltd. - Tel.: +91 11 421 42 14 • Middle East: Tarkett Middle East - Tel.: +971 21 7607 608 • New Zealand: Tarkett New Zealand Ltd. - Tel.: +64 9 236 4141 • Mexico: Tarkett S.A. - Tel.: +52 55 56 41 61 • Russia: Tarkett-France SAS, org. division - Tel.: +33 1 69 151 622 • South Africa: Tarkett-France SAS, org. division - Tel.: +33 1 69 151 622 • Switzerland: Tarkett - Tel.: +41 41 843 80 04 • Canada: Tarkett Inc. - Tel.: +1 416 291 2112 • Latin America: Brazil: Tarkett - Tel.: +55 11 3924 7100 • Argentina: Chile - Grouping: Tarkett Chile Reserco - Tel.: +56 21 53 60 717 • Peru: Tarkett Chile Reserco - Tel.: +56 21 53 60 717 • Colombia: Peru - Tarkett Chile Reserco - Tel.: +56 21 53 60 717 • Ecuador: Ecuador - Tarkett Chile Reserco - Tel.: +56 21 53 60 717 • Venezuela: Venezuela - Tarkett Chile Reserco - Tel.: +56 21 53 60 717