


Lumaflex Duo Linosport Classic



KEY POINTS

Description :

Area deformation flooring composed of:
- 18 mm interlocking plywood board to improve shock absorption, with homogeneous monolayer Linosport Classic linoleum over jute canvas backing (295 x 2430 mm slats).

- Tarfoam 1500 PU foam
- Polyethylene film

Type of installation :

Linosport Classic glued on Lumaflex Duo support.

The whole system is floating.

Installation instructions and maintenance guide :

On request

Dimensions (EN 426/EN 427) :



2 ml



28 ml

Packaging :

- **Lumaflex Duo** : 3 slats/pack, 45 packs/pallet.

- **Tarfoam 1500** : delivered in rolls. 51,25m² /pal.

- **Tarfilm** : 120 m²/rolls.

- **Skirtings** : 6 slats/pack (15m)(must be ordered).

- **Empty trapdoor** per unit (if ordered).

Total thickness (EN 428/EN 429) :



37 mm (± 3mm)

Total weight (EN 430) :



18,78 kg/m² (± 500g)

Technical data in force as from the date of publication (11/2015).

The values above correspond to laboratory test (no in situ test), and are subject to modifications for the benefit of further improvement.

For more detailed technical information, please contact Tarkett.

Colors of the products shown in the photos or samples are indicative only. There may be differences in color, gloss and embossing structure between the products sold and photos or samples.

Properties	Standards	Lumaflex Duo Linosport Classic
------------	-----------	--------------------------------

Sports properties

Friction	EN 13036-4	80-110
Shock absorption	EN 14 808	A3
Vertical deformation	EN 14 809	
Vertical ball rebound	EN 12235	97%
Specular gloss	EN ISO 2813	3 %

Classification

Reaction to fire	EN 13501-1	Cfl-S2
Formaldehyde Emission	EN 717-1 EN 717-2	E1
Pentachlorophenol	EN 12673	No pentachlorophenol

Technical Characteristics

Cigarette burns	EN 1399	Resistant
Resistance to wear	EN ISO 5470-1	≤ 1g
Resistance to indentation	EN 1516	0,40 mm
Behaviour under a rolling load	EN 1569	< 0,50mm
Resistance to impact	EN 1517	No degradation

Specific Characteristics

Surface treatment	Two-part polyurethane-based surface treatment « Classic Linofinish »		
Maintenance			

COMPATIBLE SLABS: Concrete, hot-applied asphalt and asphalt screed, anhydrite screed. Any deviation of the slab must be corrected prior installation (6 mm under a 3 m straight edge). We reserve the right to modify these specifications without, however, affecting their compliance with standards.

Linosport Classic*

91%
79%
Natural
Renewable

100%
41%
Recyclable
Recycled content

<100 µg/m³
Better Indoor
Air Quality
*TVOC AT 28 DAYS

Tarkett
ISO 14001
ENVIRONMENTAL MANAGEMENT SYSTEM
ISO 9001
QUALITY SYSTEM

WARRANTY
10
YEARS

CE
EN 14904:2006
Linosport Classic
0200-0037-DeP-2013-07
http://professionals.tarkett.com
Manufactured by: Tarkett SpA
05035 Narni - ITALY



FIBA
EQUIPMENT
& VENUE

Tarkett France – 1 terrasse Bellini – Tour Initiale TSA 94200 - 92919 Paris la Défense CEDEX
TÉL. +33(0)1 41 20 40 40 – FAX +33(0)1 41 20 47 05 – info@tarkett.com
www.professionals.tarkett.com