

# TECHNICAL DATA iD MIXONOMI

Certification & classification	Standards	iD Mixonomi																														
Type of floor covering	EN ISO 10582	Heterogeneous Compact Resilient Floorcovering																														
Classification	EN ISO 10874	Domestic: 23 Commercial: 34 Industrial: 43																														
<b>Technical characteristics</b>																																
Total thickness	EN ISO 24346	2,5 mm																														
Wear layer thickness	EN ISO 24340	0,7 mm																														
Total weight	EN ISO 23997	4000 g/m <sup>2</sup>																														
Wear layer binder content	EN ISO 10582	Type I																														
Dimensions	EN ISO 24342	<table border="0"> <tr> <td>Diamond</td> <td>38,486 x 66,66 cm</td> <td>20 planks per box = 2.56 m<sup>2</sup></td> </tr> <tr> <td>Herringbone Left</td> <td>9,62 x 38,486 cm</td> <td>80 planks per box = 2.56 m<sup>2</sup></td> </tr> <tr> <td>Herringbone Right</td> <td>9,62 x 38,486 cm</td> <td>80 planks per box = 2.56 m<sup>2</sup></td> </tr> <tr> <td>Hexagon Large</td> <td>33,33 x 38,486 cm</td> <td>20 planks per box = 1.92 m<sup>2</sup></td> </tr> <tr> <td>Hexagon Small</td> <td>20 x 23,094 cm</td> <td>60 planks per box = 2.04 m<sup>2</sup></td> </tr> <tr> <td>Rectangle</td> <td>10 x 50 cm</td> <td>75 planks per box = 3.75 m<sup>2</sup></td> </tr> <tr> <td>Square</td> <td>25 x 25 cm</td> <td>60 planks per box = 3.72 m<sup>2</sup></td> </tr> <tr> <td>Trapèze</td> <td>16,66 x 38,486 cm</td> <td>40 planks per box = 1.92 m<sup>2</sup></td> </tr> <tr> <td>Triangle Large</td> <td>38,486 x 38,486 cm</td> <td>40 planks per box = 2.56 m<sup>2</sup></td> </tr> <tr> <td>Triangle Small</td> <td>19,243 x 19,243 cm</td> <td>120 planks per box = 1.92 m<sup>2</sup></td> </tr> </table>	Diamond	38,486 x 66,66 cm	20 planks per box = 2.56 m <sup>2</sup>	Herringbone Left	9,62 x 38,486 cm	80 planks per box = 2.56 m <sup>2</sup>	Herringbone Right	9,62 x 38,486 cm	80 planks per box = 2.56 m <sup>2</sup>	Hexagon Large	33,33 x 38,486 cm	20 planks per box = 1.92 m <sup>2</sup>	Hexagon Small	20 x 23,094 cm	60 planks per box = 2.04 m <sup>2</sup>	Rectangle	10 x 50 cm	75 planks per box = 3.75 m <sup>2</sup>	Square	25 x 25 cm	60 planks per box = 3.72 m <sup>2</sup>	Trapèze	16,66 x 38,486 cm	40 planks per box = 1.92 m <sup>2</sup>	Triangle Large	38,486 x 38,486 cm	40 planks per box = 2.56 m <sup>2</sup>	Triangle Small	19,243 x 19,243 cm	120 planks per box = 1.92 m <sup>2</sup>
Diamond	38,486 x 66,66 cm	20 planks per box = 2.56 m <sup>2</sup>																														
Herringbone Left	9,62 x 38,486 cm	80 planks per box = 2.56 m <sup>2</sup>																														
Herringbone Right	9,62 x 38,486 cm	80 planks per box = 2.56 m <sup>2</sup>																														
Hexagon Large	33,33 x 38,486 cm	20 planks per box = 1.92 m <sup>2</sup>																														
Hexagon Small	20 x 23,094 cm	60 planks per box = 2.04 m <sup>2</sup>																														
Rectangle	10 x 50 cm	75 planks per box = 3.75 m <sup>2</sup>																														
Square	25 x 25 cm	60 planks per box = 3.72 m <sup>2</sup>																														
Trapèze	16,66 x 38,486 cm	40 planks per box = 1.92 m <sup>2</sup>																														
Triangle Large	38,486 x 38,486 cm	40 planks per box = 2.56 m <sup>2</sup>																														
Triangle Small	19,243 x 19,243 cm	120 planks per box = 1.92 m <sup>2</sup>																														
Surface treatment (PUR)		Yes - T opCleanXP™																														
Beveled edges		No																														
<b>Technical performances</b>																																
Dimensional stability	EN ISO 23999	≤ 0,10 %																														
Curl resultant to heat	EN ISO 23999	≤ 2 mm																														
Reaction to fire	EN 13501-1	B <sub>n</sub> -s1 glued over concrete substrate B <sub>n</sub> -s1 glued over wood substrate																														
Residual indentation	EN ISO 24343-1	≤ 0,05 mm																														
Furniture leg	EN 424	No damage																														
Castor chair	ISO 4918 - EN 425	No damage																														
Impact sound reduction	EN ISO 717-2	ΔL <sub>w</sub> = 2 dB																														
Reduction of in-room impact noise	EN ISO 31-074	Class C (L <sub>n,e,w</sub> < 85 dB)																														
Thermal resistance	EN ISO 10456	0,02 m <sup>2</sup> K/W																														
Light fastness	EN ISO 105-B02 (method 3a)	≥ 6																														
Chemical resistance	EN ISO 26987	Not affected (0)																														
Slip resistance	DIN 51130 EN 13893	R9 μ ≥ 0,30																														
Electrical properties	EN 1815 EN 1081	<2 kV on concrete > 10 <sup>9</sup> Ohm																														
Peeling resistance	EN ISO 24345	≥ 50N / 50mm																														
Underfloor heating		Suitable - max. 27 °C																														

The above information is subject to modification for the benefit of further improvement. (05/17).

Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for these instructions.

CUSTOMS TARIFF : 4820 5000 00

iD Mixonomi

