Easium

Technical data sheet

10-2016

TYPE	UNIT	FEATURE
Type of floor covering		HDF based Resilient Floor Covering
Material group		42297
Dimensions	mm	1292 x 194
Locking system	License of Välinge Innovation AB	2-Lock system
Classification	EN ISO 10874	Class 32
Commercial warranty	Years	15 years residential use

FEATURE	NORM	TARKETT TYPICAL VALUE
Technical characteristics		
Total thickness	EN ISO 24342	10 mm
Wear layer thickness	EN ISO 24340	0,4 mm
Wear layer binder content	ISO 10582	Type I
Dimension - Length	EN ISO 24342	1292 mm
Dimension - Width	EN ISO 24342	194 mm
Surface Treatment (PUR)		Yes - Extreme™
Bevelled edges		4 bevels
Technical performances		
Dimensional variation caused by changes in atmospheric humidity	EN 14085 annex C	≤ 0,40 %
Reaction to fire	EN 13501-1	Bfls1 floating on A1fl and/or A2fl substrate and on wooden sub-floor
Residual indentation	EN ISO 24343-1	≤ 0,05 mm
Furniture leg	EN 424 / ISO 16581	No damage
Castor chair	EN 425 / ISO 4918	No damage
Impact sound reduction	ISO 10140-3 / ISO 717-2	15 dB
Gaps between elements	EN 14085 annex B	o average ≤ 0,15 mm – o max ≤ 0,20 mm
Light fastness	EN ISO 105-B02	≥ 6
Height difference between elements	En 14085 / ISO 20326	h average ≤ 0,10 mm – h max ≤ 0,15 mm
Slip resistance	EN 13893 / DIN 51130	R10
Slip resistance: friction coefficient	EN 14041	≥ 0,30 – class DS
Thermal conductivity	EN 12667	Compatible with underfloor heating
Squareness	EN ISO 204342	0,2 mm
Environment		
TVOC 28 days	ISO 16000-9	<100 µg/m³
Recycled content		8,41 %
Plasticizer		Phthalate-free technology

LOGISTICS INFORMATION				
7 planks/box	1,754 m²/box	9,17 kg/m²	56 boxes/palette	98,224 m²/palette

EN 14041

32

Bfl-s1

Easium

Easium
No. 082DoP2016-07-05
http://www.home.tarkett.com
Manufactured by: Laminate Park
Werkstraße 1
66265 Heusweiler
Germany
EN 14041:2004

TARKETT BALANCED CHOICE

<100µg/m³* Better Indoor Air Quality *TVOC AT 28 DAYS

PHTHALATE FREE Technology * EXCEPT RECYCLED CONTENT

TARKETT Extreme Protection

GUARANTEE 15 YEARS Residential use

Tarkett

THE ULTIMATE FLOORING EXPERIENCE